



PRODUCT DATA SHEET

BERAM 195 LM
Hot Applied Joint Sealant

DESCRIPTION

Beram 195 LM is a high performance, hot applied, single component low modulus joint and crack sealant. **Beram 195 LM** is a very soft sealant that offers excellent low temperature bonding properties, while still maintaining a high degree of resiliency to reject incompressibles. Beram 195 LM permits high elongation at cold temperatures with low stress development. **Beram 195 LM** will not flow from the joint or be picked up by vehicle tires at high service temperatures.

RECOMMENDED USE

Beram 195 is recommended for the large scale sealing of joints and random cracks in Portland cement concrete and asphaltic concrete pavements in cold climate areas. **Beram 195 LM** was specifically formulated to provide extra protection against low temperature expansion and repeated freeze that cycles.

APPLICABLE SPECIFICATIONS

Beram 195 LM meets or exceeds:

- ASTM D-6690 Type IV (Formerly D-3405 Modified – Low Modulus)
- AASHTO: M 282-99 (ASTM D 3406-95 (2000))
- Various State and Provincial D.O.T. specifications

APPLICATION TEMPERATURES

- **Recommended Pouring Temperatures 170°C (340°F)**
- **Maximum Safe Heating Temperatures 200°C (392°F)**

APPLICATION GUIDELINES

For detailed joint and crack preparation or specific application instructions, refer to specifying agency publications or contact manufacturer representative.

MELTING EQUIPMENT

Beram 195 LM must be melted in a double boiler, oil-jacketed kettle, equipped with mechanical agitator and separate temperature thermometers for both the oil bath and melting vat.

COVERAGE

Beram 195 LM weighs approximately 9 lbs./gal (1.10 kg/L). A joint ½ x ½ " (12.7 mm x 12.7 mm) requires approximately 11 lbs. per 100 lineal feet or 16 kgs per 100 lineal meters.

PACKAGING

- 450 lb. (205 kg), open top drums containing 10 individual 50 lb. pucks
- 2 x 25 lb. Polybags in a high strength corrugated cardboard container
- 50 lb. steel pails

BERAM 195

LOW MODULUS HOT APPLIED JOINT SEALANT

PHYSICAL PROPERTIES
BERAM 195 LOW MODULUS HOT APPLIED JOINT SEALANT

ASTM D-6690 Type IV (Formerly D-3405 Modified – Low Modulus)

PROPERTIES	TEST METHODS	SPECIFICATIONS	TYPICAL RESULTS
Penetration @ 25°C 150 G, 5 sec.	ASTM D-5329	90 – 150	120
Flow @ 60°C	ASTM D-5329	3 MM MAX.	1.0
Bond @ -29°C 200% ext – ½"	ASTM D-5329	PASS 3 CYCLES	PASS
Resiliency @ 25°C	ASTM D-5329	60% MIN.	70%
Asphalt Compatibility	ASTMD-5329	PASS	PASS
Ductility @ 25°C	ASTM D-113	-	50 CM
Prolonged Heating (after 6 hours @ pouring temp)	ASTM D-3407	PASS ALL REQUIREMENTS	PASS
Min softening point	ASTM D-36	Min. 80°C	84°C

McAsphalt Industries Ltd.
8800 Sheppard Avenue East
Toronto, Ontario M1B 5R4
Tel: (416) 281-8181 Fax: (416) 281-8842
Email: info@mcasphalt.com